

RT153FC



High Temperature Epoxy Adhesive

Description

RT153FC is a fast cure version of the industry standard adhesive for "pot and polish" fibre optic connections.

Benefits

- Glass transition temperature greater than 100°C, giving outstanding temperature performance
- High surface energy and low viscosity. Readily wets and wicks between optical fibres
- Excellent adhesion to glass fibres as well as metals, ceramics and many plastics
- Outstanding impact and thermal shock resistance
- Colour change on cure from straw through amber to red
- Excellent moisture and chemical resistance
- Available in 4g TwinPack sachets, and bulk packs

Typical Properties

Mix ratio:	1 part hardener to 8 parts resin
Mixed viscosity:	1 – 3 Pa.s (1000 – 3000 cPs)
Work life:	4 hours @ 23°C (4g in syringe)
Surface Tension:	42 - 44 mN/m
Curing Schedule:	85°C for 15 minutes 105°C for 5 minutes 125°C for 2 minutes

Optimum Performance (cured for 5 minutes at 105°C)

Glass Transition:	>100°C
Refractive Index:	1.55
Density:	1.15
Hardness:	85 D
Modulus:	1 Gpa
Operating Temperature:	-60 to 200°C
Lap Shear – Al/Al	11 MPa (@ 23°C)

Related Products

- The Resintech fibre optic adhesive range

Issue 2 - April 2005

Resintech Limited warrants only that its products meet the specifications stated herein. Typical properties where stated are to be considered as representative of the current production and should not be treated as specifications. While the information presented is believed to be true and reliable, users are advised to conduct sufficient investigations to ensure the suitability of any product for its intended use. Resintech Limited cannot accept any responsibility for loss or damage that may result from the use of this information.

Resintech Limited

Horcott Industrial Estate, Fairford, Gloucestershire, GL7 4BX, United Kingdom

t: +44 (0)1285 712755 f: +44 (0)1285 712999 e: technical@resintech.co.uk w: www.resintech.co.uk